

## Visqueen Zedex Housing Grade DPC Cavity Tray

### Features & benefits

- BBA certified - third party accreditation
- Assessed in accordance with Technical Requirement R3 - conforms to NHBC requirements and suitable for NHBC sites
- Widths from 100mm to 900mm
- Visqueen Preformed Units available - simplifies complex or awkward detailing

### Product description

Visqueen Zedex Housing Grade Damp Proof Course (DPC) is a black, flexible 0.6mm damp proof course and cavity tray system. It is manufactured from a mixture of thermoplastic polymers and additives including elastomers. The product does not conform to BS6515:1984.

The DPC is supplied in 20m length rolls and the following widths: 100mm, 112.5mm, 150mm, 225mm, 300mm, 337.5mm, 450mm, 600mm, 750mm and 900mm.

### Approvals and standards

- Third party accreditation (BBA 94/3059)
- UKCA UKNI CE to EN 14909:2012 Type A
- Visqueen certified with Quality Management System ISO 9001:2015
- Visqueen certified with Occupational Health and Safety System ISO 45001:2018
- Visqueen certified with Environmental Management System ISO 14001:2015

### Usage

Visqueen Zedex Housing Grade Damp Proof Course is designed for residential buildings up to and including 3 storeys high. The DPC is suitable for installation in internal walls to prevent rising damp. The DPC is also suitable for installation in external cavity walls with a masonry outer leaf, including walls with a light gauge steel frame, structural timber frame or masonry inner leaf. The DPC can be site formed into built-in or surface fixed cavity trays to manage the downward passage of water in cavity wall applications. When used as a cavity tray, the DPC should be fully supported along its length e.g. supported by the lintel or supported by full-fill insulation. The DPC can also be used on sleeper walls below a ground floor construction e.g. beam and block floor system.

### System components

- Visqueen Zedex DPC Surface Fixing System
- Visqueen HP Tanking Primer, 5L
- VisqueenPro Detailing Strip, 300mm x 10m
- Visqueen 100mm Double Sided Butyl Tape, 100mm x 15m

### Storage and handling

Visqueen Zedex Housing Grade Damp Proof Course should be stored vertically, under cover in its original packaging.

Care should be taken when handling the product in line with current manual handling regulations.

### Preparation

The Visqueen Zedex Housing Grade Damp Proof Course can be cut with a sharp retractable safety knife or robust scissors.

### Installation

DPCs and DPC cavity trays systems to be designed and installed in accordance with the relevant sections of BS 8215:1991, PD 6697:2019 and BS 8000-3:2020.

When built into a masonry wall construction Visqueen Zedex Housing Grade Damp Proof Course should be installed on an even bed of wet mortar, and any perforations in adjacent courses of masonry should be completely filled with mortar. To ensure mortar adhesion, as soon as possible after laying the DPC, lay at least one further course of masonry including a bed of mortar. If positioned on the sleeper walls below a suspended ground floor e.g. beam and block floor system, the DPC can be dry laid, however all sharp protrusions must be removed from the substrate. The DPC must extend through the full thickness of the masonry wall, including pointing, applied rendering or other facing materials.

When used as a site formed cavity tray, the DPC can be either built-in to the inner leaf or surface fixed to the cavity face of the inner leaf. The DPC should be supported along its length e.g. supported by the lintel or full-fill insulation.

When surface fixing the cavity tray, the substrate should be primed with Visqueen HP Tanking Primer and allowed to dry. The DPC should be bonded to the inner leaf using Visqueen 100mm Double Sided Butyl Tape and

## Visqueen Zedex Housing Grade DPC Cavity Tray

permanently secured using Visqueen Fixing Strip and fixings suitable for the substrate. Visqueen Fixing Pins for the rigid urethane foam insulation of a SFS substrate, and fixing pins for a masonry substrate are available.

When using a hammer tacker to secure the DPC to an OSB3 substrate of a timber frame construction, minimum 8mm shank austenitic stainless steel staples should be used at minimum 150mm centres.

To simplify complex or awkward junctions e.g. corners, changes of level, arch windows etc, an extensive range of Visqueen Preformed Units are available.

All DPC to DPC laps and DPC to Visqueen Preformed Unit laps should be a minimum of 100mm and bonded with Visqueen 100mm Double Sided Butyl Tape.

### Usable temperature range

It is recommended that Visqueen Zedex Housing Grade Damp Proof Course and all associated system components should not be installed below 5°C.

### Additional information

Where a high performance DPC is required e.g for commercial or multi storey constructions, use Visqueen Zedex CPT High Performance Damp Proof Course.

Where a gas DPC conforming to the specification requirements of BS 8485:2015 + A1:2019 is required, use Visqueen Ultimate Gas Damp Proof Course.

For built-in internal and external corners Visqueen Preformed Corner Units should be used see PFU-553 (90° unit) or PFU-501 (sloping unit).

For surface fixed internal and external corners Visqueen Preformed Corner Units should be used see PFU-554 (90° unit) or PFU-502 (sloping unit).

For additional detailing information, contact Visqueen Technical Services +44 (0) 333 202 6800

The information in this datasheet was correct at the time of publication. It is the user's responsibility to obtain the latest version of the datasheet as it is updated on a regular basis. The information contained in the latest datasheet supersedes all previously published editions.

| Property                               | Test method               | Units            | Compliance criteria | Result      |
|--|---------------------------|------------------|---------------------|-------------|
| Visible defects                        | BS EN 1850 -2             | -                | Pass/Fail           | Pass        |
| Width                                  | BS EN 1848-2              | mm               | -5%/+5%             | 100 to 1400 |
| Straightness                           | BS EN 1848-2              | -                | Pass/Fail           | Pass        |
| Thickness                              | BS EN 1849-2              | micron           | -10%/+10%           | 600         |
| Mass                                   | BS EN 1849-2              | g/m <sup>2</sup> | -10%/+10%           | 570         |
| Joint strength                         | BS EN 12317-2             | N/50mm           | >MLV                | 160         |
| Watertightness to 2kPa for 24 hours    | BS EN 1928                | -                | Pass/Fail           | Pass        |
| Tensile strength (MD)                  | BS EN 12311-2             | MPa              | >MLV                | 17          |
| Tensile strength (TD)                  | BS EN 12311-2             | MPa              | >MLV                | 14          |
| Elongation (MD)                        | BS EN 12311-2             | %                | >MLV                | 500         |
| Elongation (TD)                        | BS EN 12311-2             | %                | >MLV                | 500         |
| Resistance to impact                   | BS EN 12691               | mm               | >MLV                | 200         |
| Flexibility at low temperatures        | BS EN 1109                | °C               | MDV                 | -15         |
| Durability (artificial ageing)         | BS EN 1296 and BS EN 1928 | -                | Pass/Fail           | Pass        |
| Durability chemical resistance         | BS EN 1847                | -                | Pass/Fail           | Pass        |
| Durability against alkali - annex c    | BS EN 14909               | -                | Pass/Fail           | Pass        |
| Resistance to tearing (nail shank) MD  | BS EN 12310-1             | N                | MDV                 | 320         |
| Resistance to tearing (nail shank) TD  | BS EN 12310-1             | N                | MDV                 | 310         |
| Water vapour transmission - resistance | BS EN 1931                | MNs/g            | MDV                 | 365         |

## Visqueen Zedex Housing Grade DPC Cavity Tray

|  |               |                     |     |      |
|--|---------------|---------------------|-----|------|
| Water vapour transmission - permeability | BS EN 1931    | g/m <sup>2</sup> /d | MDV | 0.37 |
| Reaction to fire                         | BS EN 13501-1 | Class               | MDV | F    |

### Health and safety information

Refer to the Visqueen Zedex Housing Grade Damp Proof Course safety datasheet (SDS).

### About Visqueen


Visqueen is a leading provider of construction membrane technologies and design-based solutions for ground gas, structural waterproofing, damp proofing and fire protection.

We offer complete support at every stage of the specification, including the supply chain process. As the UK's principal technical authority, we are best placed to ensure that the principal designer and contractor specify the most technically suited, durable, and competitive solution to guarantee their project is protected for the lifetime of the building.

Visqueen is at the forefront of advanced membrane technology and innovation in the construction industry, earning the trust and loyalty of specifiers throughout the UK and Europe.

For more information, visit [visqueen.com](http://visqueen.com) or contact our sales office at [+44 \(0\) 333 202 6800](tel:+44(0)3332026800) or [enquiries@visqueen.com](mailto:enquiries@visqueen.com)

### Complete Range, Complete Solution



### Visqueen Technical Support

Visqueen offer a comprehensive full nationwide technical support. Our team of CSSW qualified technical support managers provide on site design-based solutions for specifiers, contractors and builders merchants, and will ensure that from design stage to installation the project is fully risk assessed and the specification is approved by all stakeholders.

Our Technical Office, can design, prepare and manage CAD detailing, together with assisting in quantity take offs, while offering advice on technical installations and product selection.

### Competency & Design

Visqueen promotes competency in building design by ensuring that its technical team possesses the necessary skills, knowledge, experience, and ethical practices. The company adopts the "golden thread of information," ensuring all project data is digitally secure and accessible throughout a building's lifecycle. This approach aligns with the Building Safety Act and aims to foster accountability and compliance with evolving regulations, providing clients with confidence in the safety and reliability of their projects.

### Visqueen CPD Seminars

Visqueen's CPD Seminars offer insights into Building Regulations, Standards, and industry guidance related to damp proofing, hazardous ground gas protection, and structural waterproofing. These one-hour seminars are tailored for construction design professionals and delivered by our Technical Support Managers. Visit our website to book a free CPD.

### Visqueen Contract Design Services

Visqueen Contract Design Services offers a bespoke design service led by our team of Certified Surveyors in Structural Waterproofing (CSSW), providing experienced and specialised waterproofing design expertise for complex projects. We provide comprehensive support throughout the entire project, ensuring that all work meets the requirements of warranty providers and adheres to the highest standards of quality, reliability and current legislation.

### Visqueen Training Academy

Based at our Derbyshire facility, the Visqueen Training Academy offers a variety of training programs across the

## Visqueen Zedex Housing Grade DPC Cavity Tray

UK. These include one-day product awareness sessions for distributors and builders' merchants, and intensive two-day courses for hands-on product installation training. Contact us for more information.

---