

Visqueen RadonBlok 600

Features & benefits

- Agreement certified - third party accreditation
- Complies with NHBC Foundation's NF94 guidance for radon protection in Type A, Type B and Type C membrane locations
- Conforms to BR 211:2023 - industry guidance for radon protection
- Also provides damp proof membrane protection
- Dual jointing methods - lap joints can be taped or heat welded

Product description

Visqueen RadonBlok 600 is a flexible 0.6mm thick thermoplastic membrane. The product is purple in colour and supplied 2m x 25m in a single wound roll (not folded).

The membrane is manufactured from virgin polymer.

Approvals and standards

- Third party accreditation (IAB certificate 05/0214)
- Complies with NHBC Foundation's NF94 guidance for radon protection in Type A, Type B and Type C membrane locations
- Conforms to the specification requirements of BR 211:2023
- UKCA UKNI CE to EN 13967:2017
- Visqueen certified with Quality Management System ISO 9001:2015
- Visqueen certified with Occupational Health and Safety System ISO 45001:2018
- Visqueen certified with Environmental Management System ISO 14001:2015

Usage

Visqueen RadonBlok 600 is used to prevent the ingress of radon in both basic and full radon protection areas. The membrane can be positioned within the ground floor construction either above or below the structural floor.

Radon protection - NHBC NF94 guidance:
Visqueen RadonBlok 600 when installed with either taped or welded joints complies with NHBC Foundation's NF94 publication, Hazardous ground gas - an essential guide for housebuilders, in Type A membrane locations. The membrane also complies with this guidance when installed with welded joints in Type B and Type C membrane locations. For further information, contact Visqueen Technical Office.

The product is not intended for use where there is a risk of hydrostatic pressure.

System components

- VisqueenPro Detailing Strip, 300mm x 10m, 500mm x 10m
- VisqueenPro Single Sided Tape, 75mm x 25m
- Visqueen Top Hat Units
- Visqueen RadonBlok Double Sided Tape, 30mm x 30m
- Visqueen GR Lap Tape, 150mm x 10m
- Visqueen Radon Sump
- Visqueen NF-Detailing Strip, 300mm x 10, 500mm x 10m

Storage and handling

Visqueen RadonBlok 600 should be stored horizontally, under cover in its original packaging.

Care should be taken when handling the product in line with current manual handling regulations.

Preparation

Visqueen RadonBlok 600 should be installed on a smooth continuous surface e.g. grouted beam and block floor, a compacted blinding layer e.g. 50mm thick sand blinding, or smooth concrete blinding. The substrate should be free from irregularities such as voids or protrusions.

The membrane can be cut with a sharp retractable safety knife or robust scissors.

When installing the membrane in demanding site conditions, use Visqueen GR Lap Tape in place of VisqueenPro Single Sided Tape.

Installation

Visqueen RadonBlok 600 should be loose laid on the substrate. The membrane should be clean and dry at the time of jointing. It should be overlapped by at least 150mm, bonded with Visqueen RadonBlok Double Sided Tape and sealed with VisqueenPro Single Sided Tape. Alternatively lap joints can be heat welded to achieve an effective seal. The overlap in the barrier is typically 100mm and when hand welding, a 35mm weld is normally achieved. When

Visqueen RadonBlok 600

hand welding, a roller must be used.

Airtight seals should be formed around all service entry points. Visqueen Preformed Top Hat Units should be used for sealing service entry pipes. The base of the top hat and the upstand should be bonded using Visqueen RadonBlok Double Sided Tape and sealed with VisqueenPro Single Sided Tape. The upstand should be secured with the supplied jubilee clip. Alternatively VisqueenPro Detailing Strip or Visqueen NF-Detailing Strip can be used to seal service entry points. The upstand should be secured with a jubilee clip.

Forming an effective barrier to radon may give rise to complex three-dimensional detailing where, it is recommended Visqueen Preformed Units are used e.g. corners. Alternatively VisqueenPro Detailing Strip or Visqueen NF-Detailing Strip can be used to seal awkward junctions.

If the membrane is punctured or perforated a patch of the same material should be lapped at least 150mm beyond the limits of the puncture and bonded with Visqueen RadonBlok Double Sided Tape and sealed with Visqueen Pro Single Sided Tape. Alternatively a patch can be formed using VisqueenPro Detailing Strip or Visqueen NF-Detailing Strip and lapped at least 150mm beyond the extents of the puncture.

Long periods of exposure to ultraviolet light will reduce the effectiveness of the membrane. The membrane should be covered by a protective layer immediately after installation to prevent damage from following trades, ultraviolet light, etc. Care should be taken to ensure that the membrane is not punctured, stretched or displaced when applying a screed or final floor covering. A minimum thickness of 50mm screed is recommended.

When reinforced concrete is to be laid over the membrane the wire reinforcements and spacers must be prevented from puncturing the membrane. Where there is a high risk of potential damage, the membrane should be covered with Visqueen TreadGUARD protection, screed, or other approved protection material before positioning the reinforcement.

When used in full radon protection areas, a Visqueen Radon Sump or subfloor ventilation system maybe required.

Usable temperature range

When taping joints, it is recommended that Visqueen RadonBlok 600 and all associated system components should not be installed below 5°C.

Additional information

Where ground gas protection is required to BS 8485:2015 + A1:2019, use Visqueen Gas Barrier or Visqueen Gas Barrier NF-400 systems.
To assist build sequencing, Visqueen Zedex CPT DPC is available for radon protection through the wall constructions.

For additional detailing information, contact Visqueen Technical Services +44 (0) 333 202 6800.

The information in this datasheet was correct at the time of publication. It is the user's responsibility to obtain the latest version of the datasheet as it is updated on a regular basis. The information contained in the latest datasheet supersedes all previously published editions.

Property	Test method	Units	Compliance criteria	Result
Length	BS EN 1848-2	m	-1	25
Width	BS EN 1848-2	m	-1	2
Straightness	BS EN 1848-2	-	Pass/Fail	Pass
Thickness	BS EN 1849-2	mm	-1	0.6
Tensile strength - MD	BS EN 12311	N/mm ²	MDV	15
Tensile strength - CD	BS EN 12311	N/mm ²	MDV	15
Tensile elongation - MD	BS EN 12311	%	MDV	400
Tensile elongation - CD	BS EN 12311	%	MDV	400
Joint strength	BS EN 12317-2	N	MLV	400
Watertightness to 2kPa for 24 hours	BS EN 1928	-	Pass/Fail	Pass
Resistance to impact	BS EN 12691	mm	MDV	200
Durability (artificial ageing)	BS EN 1296 and BS EN 1928	-	Pass/Fail	Pass
Durability chemical resistance	BS EN 1847	-	Pass/Fail	Pass

Visqueen RadonBlok 600

Resistance to tearing (nail shank) MD	BS EN 12310-1	N	MDV	345
Resistance to tearing (nail shank) CD	BS EN 12310-1	N	MDV	340
Water vapour transmission - resistance	BS EN 1931	MNs/g	MDV	1188
Water vapour transmission - permeability	BS EN 1931	g/m ² /d	MDV	0.12
Diffusion equivalent air layer thickness	BS EN 1931	m	MDV	238
Low temperature flexibility	BS EN 495-5	°C	MDV	-25
Radon Transmission Rate	SP test method	m ² /s	MDV	5.7 x 10 ⁻¹²
Methane gas transmission rate	ISO 15105-1	ml/m ² /day/atm	MDV	300
Visible defects	BS EN 1850 -2	-	Pass/Fail	Pass
Reaction to fire	BS EN 13501-1	Class	MDV	E

Health and safety information

Refer to the Visqueen RadonBlok 600 safety datasheet (SDS).

About Visqueen

Visqueen is a leading provider of construction membrane technologies and design-based solutions for ground gas, structural waterproofing, damp proofing and fire protection.

We offer complete support at every stage of the specification, including the supply chain process. As the UK's principal technical authority, we are best placed to ensure that the principal designer and contractor specify the most technically suited, durable, and competitive solution to guarantee their project is protected for the lifetime of the building.

Visqueen is at the forefront of advanced membrane technology and innovation in the construction industry, earning the trust and loyalty of specifiers throughout the UK and Europe.

For more information, visit [visqueen.com](https://www.visqueen.com) or contact our sales office at +44 (0) 333 202 6800 or enquiries@visqueen.com

Complete Range, Complete Solution



Passive Fire Protection



Gas Protection



Damp Proof Membrane



Air and Vapor Control



Stormwater



Damp Proof Course



Temporary Protection

Visqueen Technical Support

Visqueen offer a comprehensive full nationwide technical support. Our team of CSSW qualified technical support managers provide on site design-based solutions for specifiers, contractors and builders merchants, and will ensure that from design stage to installation the project is fully risk assessed and the specification is approved by all stakeholders.

Our Technical Office, can design, prepare and manage CAD detailing, together with assisting in quantity take offs, while offering advice on technical installations and product selection.

Competency & Design

Visqueen promotes competency in building design by ensuring that its technical team possesses the necessary skills, knowledge, experience, and ethical practices. The company adopts the "golden thread of information," ensuring all project data is digitally secure and accessible throughout a building's lifecycle. This approach aligns with the Building Safety Act and aims to foster accountability and compliance with evolving regulations, providing clients with confidence in the safety and reliability of their projects.

Visqueen CPD Seminars

Visqueen's CPD Seminars offer insights into Building Regulations, Standards, and industry guidance related to damp proofing, hazardous ground gas protection, and structural waterproofing. These one-hour seminars are tailored for construction design professionals and delivered by our Technical Support Managers. Visit our website

Visqueen RadonBlok 600

to book a free CPD.

Visqueen Contract Design Services

Visqueen Contract Design Services offers a bespoke design service led by our team of Certified Surveyors in Structural Waterproofing (CSSW), providing experienced and specialised waterproofing design expertise for complex projects. We provide comprehensive support throughout the entire project, ensuring that all work meets the requirements of warranty providers and adheres to the highest standards of quality, reliability and current legislation.

Visqueen Training Academy

Based at our Derbyshire facility, the Visqueen Training Academy offers a variety of training programs across the UK. These include one-day product awareness sessions for distributors and builders' merchants, and intensive two-day courses for hands-on product installation training. Contact us for more information.
