

## Visqueen Self Adhesive Membrane

### Features & benefits

- BBA certified - third party accreditation
- Type A Barrier Membrane (Tanking Membrane) - resistant to ground water in accordance with BS 8102:2022
- Also provides radon and damp proof membrane protection
- Self adhesive application - no jointing tapes required

### Product description

Visqueen Self Adhesive Membrane is a modified bitumen rubber membrane with a self adhesive coating protected by a removable polyethylene release film. It is dark grey on the upper surface and supplied in rolls 1m x 20m.

### Approvals and standards

- Third party accreditation (BBA 15/5208)
- Suitable for use as a Type A Barrier Membrane (Tanking Membrane) to BS 8102:2022
- Conforms to the specification requirements of BR 211:2023
- UKCA UKNI CE to EN 13969:2004
- Visqueen certified with Quality Management System ISO 9001:2015
- Visqueen certified with Occupational Health and Safety System ISO 45001:2018
- Visqueen certified with Environmental Management System ISO 14001:2015

### Usage

Visqueen Self Adhesive Membrane is a cold applied product, suitable for use as a Type A Barrier Membrane (Tanking Membrane) for above and below ground applications e.g. basements, retaining walls and lift pits. The membrane can be applied to a variety of substrates including concrete, flush pointed blockwork, flush pointed brickwork, particle boards and steelwork, in both vertical and horizontal applications.

The membrane can be used to achieve one form of waterproofing to Grades 1, 2 and 3 as defined in BS 8102:2022.

### System components

- Visqueen HP Tanking Primer, 5L
- Visqueen Pile Cap Sealer, 25kg
- Visqueen Top Hat Units
- Visqueen TreadGUARD 1500, 1m x 2m
- Visqueen IGW5 and IGW10 Waterstops

### Storage and handling

Visqueen Self Adhesive Membrane should be stored vertically under cover in its original packaging.

Care should be taken when handling the product in line with current manual handling regulations.

### Preparation

All surfaces to which Visqueen Self Adhesive Membrane are to be applied should be free from cavities or projections, have a smooth finish, be dry and free from dust, loose particles and frost. Masonry, concrete or metal surfaces should be primed using Visqueen HP Tanking Primer and allowed to dry thoroughly.

When applying to blockwork or brickwork the joints must be flush pointed or the masonry rendered prior to applying the membrane.

The membrane can be cut with a sharp retractable safety knife.

### Installation

Visqueen Self Adhesive Membrane lap joints should be a minimum of 150mm and should be pressed and rolled to form a continuous bond and to ensure watertightness.

At 90 degree changes of direction a Visqueen Axiom UniSeal fillet should be formed prior to membrane installation.

For vertical applications cut the membrane to a suitable length allowing an additional 150mm for laps. Position and peel back release film and apply the self adhesive face to the substrate. Apply pressure to ensure a full bond is achieved. Commence at the top of the wall and work downwards, progressively removing the release film.

For horizontal applications unroll the membrane where required allowing an additional 150mm for laps. Re-roll one half of the membrane and cut release film taking care not to damage the membrane. Roll out the membrane progressively removing the release film. Use a soft broom over the top of the membrane to ensure full adhesion to the substrate. Repeat for the other half of the roll.

Watertight seals should be formed around all service entry points. Visqueen Preformed Top Hat Units should be

## Visqueen Self Adhesive Membrane

used for sealing service entry pipes.

If the membrane is punctured or perforated, a patch of the same material should be lapped and bonded at least 150mm beyond the extents of the puncture.

The membrane should always be fully protected immediately after it is installed. When used externally on a retaining wall, the membrane should be protected from backfill with Visqueen TreadGUARD 1500. Alternatively, where external drainage is also required the membrane can be protected with Visqueen Protect&Drain.

When forming day joints, the upper edge of the membrane should be adequately secured e.g. bonding onto the top of the retaining wall, or if terminated on a vertical face, the upper edge should be secured with Visqueen Fixing Strip and Visqueen Fixings Pins for Masonry.

### Usable temperature range

It is recommended that Visqueen Self Adhesive Membrane and all associated system components should not be installed below 5°C.

The membrane requires no additional bonding methods however during cold weather conditions the application of hot air to the self adhesive coating will aid adhesion.

### Additional information

Where hazardous ground gases are present use Visqueen Gas Resistant Self Adhesive Membrane  
 Where concrete construction joints occur Visqueen IGW Waterstop system should be incorporated  
 Where wall ties penetrate the membrane, seal with Visqueen Axiom UniSeal  
 When waterproof concrete is required, or for additional detailing information, contact Visqueen Technical Services +44 (0) 333 202 6800.

The information in this datasheet was correct at the time of publication. It is the user's responsibility to obtain the latest version of the datasheet as it is updated on a regular basis. The information contained in the latest datasheet supersedes all previously published editions.

Characteristic	Test method	Units	Compliance criteria	Value or statement
Length	BS EN 1848-2	m	0%/+5%	20
Width	BS EN 1848-2	m	-5%/+5%	1
Thickness	BS EN 1849-2	mm	-5%/+10%	1.5
Mass	BS EN 1849-2	g/m <sup>2</sup>	-10%/+10%	1650
Watertightness to 60kPa for 24 hours	BS EN 1928	kPa	MDV	Pass
Durability after artificial ageing)	BS EN 1847	-	Pass/Fail	Pass
Durability against chemicals	BS EN 1847	-	Pass/Fail	Pass
Resistance to tearing (nail shank) MD	BS EN 12310-1	N	>	100
Resistance to tearing (nail shank) CD	BS EN 12310-1	N	>	100
Water vapour transmission properties	BS EN 1931	g/m <sup>2</sup> /d	MDV	0.09
Resistance to static loading	BS EN 12730	kg	>MLV	20
Resistance to Impact method A and B	BS EN 12691	mm	>	A >500 B >1000
Joint resistance	BS EN 12317-1	N	>	30
Tensile properties - MD	BS EN 12311-2	N/mm <sup>2</sup>	>	2.5
Tensile properties - CD	BS EN 12311-2	N/mm <sup>2</sup>	>	2.5
Tensile elongation - MD	BS EN 12311-1	%	>	130
Tensile elongation - CD	BS EN 12311-2	%	>	130
Radon permeability	SP Method	m <sup>2</sup> /s	MDV	5.7x10 <sup>-12</sup>
Reaction to fire	BS EN 13501-1	Class	MDV	F



## Visqueen Self Adhesive Membrane

Visqueen's CPD Seminars offer insights into Building Regulations, Standards, and industry guidance related to damp proofing, hazardous ground gas protection, and structural waterproofing. These one-hour seminars are tailored for construction design professionals and delivered by our Technical Support Managers. Visit our website to book a free CPD.

---

### Visqueen Contract Design Services

Visqueen Contract Design Services offers a bespoke design service led by our team of Certified Surveyors in Structural Waterproofing (CSSW), providing experienced and specialised waterproofing design expertise for complex projects. We provide comprehensive support throughout the entire project, ensuring that all work meets the requirements of warranty providers and adheres to the highest standards of quality, reliability and current legislation.

---

### Visqueen Training Academy

Based at our Derbyshire facility, the Visqueen Training Academy offers a variety of training programs across the UK. These include one-day product awareness sessions for distributors and builders' merchants, and intensive two-day courses for hands-on product installation training. Contact us for more information.

---